

ERS[™]200

Epoxy Resin Saturant



Building
&
Transportation



Oil, Gas
&
Industrial



Offshore
&
Onshore



Water
&
Wastewater



PRODUCT DESCRIPTION

The CTech-LLC[®] Epoxy Resin Saturant (ERS[™]200) is epoxy matrix materials for saturating composite fibers and bonding applications. ERS[™]200 is available in forms of liquid. The reaction of epoxy with hardener results an outstanding durability material which is a proper matrix for all of the composite systems and structural strengthening works. CTech-LLC[®] epoxy resins offer a wide range of high performance properties like excellent chemical and mechanical resistance and strong adhesion. ERS[™]200 epoxy resins can be used in different fields like strengthening and retrofitting of structural members, making composite components for automobiles, producing industrial tools and many other important fields.

ADVANTAGES

- CTech-LLC[®] ERS[™]200 epoxy resin have higher strength compared with other epoxy materials.
- ERS[™]200 epoxy resins are extremely durable and resistant to temperature and moisture. They also have high fatigue strength.
- ERS[™]200 epoxy resins have high mechanical and chemical resistance.
- ERS[™]200 epoxy resins have high adhesive strength and in addition to high saturation capability can be used for bonding an extended range of elements and materials like FRP sheets, metal elements, plastics and many other types of materials and elements.
- ERS[™]200 epoxy resin is easy to use and can be known as an eco-friendly product.
- ERS[™]200 epoxy resins have high dielectric performance and are resistant to electricity.
- Curing of ERS[™]200 epoxy resin is very quick and convenient.

TYPICAL USES

- ERS[™]200 epoxy resins are high-performance adhesives which are widely used in strengthening and retrofitting of different types of structures and manufacturing composite products.
- Epoxy resins are electrical insulators, so they are highly used in electrical industry. ERS[™]200 epoxy resins can be used in manufacturing many of the electrical components like motors and generators.
- Today using epoxy resins is an effective method for bonding different components of automobiles, so we can employ them in the assembly of different parts like sun roofs, side view mirrors, spoilers

and many other important parts.

- Epoxy resins are widely used in aerospace industry. We can use these powerful resins to assemble or repair interior and exterior aircraft components.
- ERS[™]200 epoxy resins can be useful in marine industry. They are ideal materials for repairing different parts of ships such as underwater hulls, ballast, tanks, cargo tanks and superstructures.
- Most of the wind turbine rotor blades are made from epoxy resins. Because of their strong adhesion and durability, epoxies can be suitable materials for turbine blades.

INSTALLATION PROCEDURE

SURFACE PREPARATION

- For retrofitting applications, substrate preparation can highly effect on the quality of the performance of CFRP and GFRP composite systems.
- All the surfaces must be cleaned from dirt, grime, dust, curing compounds, oils, grease, waxes and all the other contaminated materials which may cause voids behind the CTech-LLC[®] composites.
- Repair mortar must be used to repair all the eroded or damaged concrete surfaces.
- An industrial vacuum cleaner must be used to remove dust and dirt.
- All the surfaces need grinding, sandblasting, shot blasting, pressure wash or other common mechanical methods to reach an even concrete substrate.

- The edges must be smooth and rounded to a minimum radius of 30 mm

EPOXY COMPONENT PHYSICAL PROPERTIES

Chemical Base	Epoxy resin
Net Weight	Component A = 20 Kg Component B = 2.6 Kg
Mixing Ratio	100:13 Part A: 100 Part B: 13
Viscosity	Component A at 21° C is 8000-11000 cps Component B at 21° C is 200 cps Viscosity of mixed product 700-800 cps
Pot Life	25 to 30 Minutes at 21° C
Density at 21o C ASTM D792	Component A = 1.16kg/L Component B = 0.95kg/L Mixed product =1.11kg/L
Application Methods	Hand lay-up, Spray machine and Robot processes
Shelf Time	24 month
Storage Condition	dry and away from direct sunlight 10-40°C

EPOXY MATERIAL MECHANICAL PROPERTIES

Property	ASTM Method	Test Value*
Epoxy Equivalent Part A	D1652	185-192 g/eq
Epoxy Value Part A	D1652	0,51-0.54 mol/100g
Hydrolysable Chlorine Part A	D1726	Max 0.1 wt %
Nonvolatile Part A	DIN EN ISO 3251	Min 99 wt %
Tg	D4065	82° C
Tensile Strength	D638 Type1	<35 MPa
Tensile Modulus	D638 Type1	<3.1 GPa
Elongation Percent	D638 Type1	<2.0 %
Compressive Strength	D695	<60 MPa
Compressive Modulus	D695	<3.2 GPa

* Curing schedule 72 hours post cure at 60o C.

* Testing temperature: 21°C

MIXING

Epoxy compounds are usually supplied in two different containers. Before pouring the contents of component B into contents of component A, each part should be stirred separately to avoid deposit in container. Then part A and B should be mixed together depending

on the required quantity. Process of mixing should take 3-5 minutes with a low speed mixer. After mixing resin and hardener, you'll have about 25-30 minutes time to apply the material. Clean mixing tools with a proper towel to reuse them.

APPLICATION

Surface of all the contaminated elements must be cleaned thoroughly. Prime the surface with a suitable type of CTech-LLC® primer. ERS™200 epoxy resins are compatible with all types of CTech-LLC® fabrics, primers and mortars. Mix part A and B together with a low speed mixer.

You can use saturators for impregnating fabrics or apply hand methods for some of the smaller projects. Using a roller can help to eliminate air bubbles in the resin and substrate, it can also ensure that there is a good bonding between them.

STORAGE & SHELF LIFE

ERS™200 must be stored in a dry and cool place. Temperature should be between 5° to 35° C. Avoid freezing the product and keep it away from direct sunlight, flame or other hazards.

CAUTION

All components of FRP composite systems may cause skin irritation and sensitization. Use of chemical resistant gloves is recommended.

Avoid breathing vapors and dust. Get medical attention if you are breathing with difficulty.

CTech-LLC®

CYTEC's Composite Technology

technical@ctech-llc.com
info@ctech-llc.com
www.CTech-LLC.com

IMPORTANT NOTE:

Before using any CTech-LLC® product, the user must review the most recent version of the product's technical data sheet, material safety data sheet and other applicable documents, available at www.ctech-llc.com.

WARANTY:

CTech-LLC® warrants its products to be free from manufacturing defects. Buyer determines suitability of product for use and assumes all risks. Buyer's sole remedy shall be limited to replacement of product. Any claim for breach of this warranty must be brought within one month of the date of purchase. CTech-LLC® shall not be liable for any consequential or special damages of any kind, resulting from any claim or breach of warranty, breach of contract, negligence or any legal theory. The Buyer, by accepting the products described herein, agrees to be responsible for thoroughly testing any application to determine its suitability before utilizing.